

Technical Data **Mini Surelight EL Wire**



Grade: Mini	Standard Diameter Ø (mm)	Chromaticity		Brightness		Twisting Angle ° (Degrees)/m	Stretching Force Kg	Bending Diameter mm	Operating temperature °C (Degrees)	Lifetime* 100VAC & 400Hz Hours
		100V X	400Hz Y	100V 120V 2000Hz Cd/m ²						
Colour		X	Y							
Lime	Ø 1.2	0.319	0.628	116.8	188.0	30	0.5	10	- 20 to 55	5700
Red	Ø 1.2	0.682	0.315	20.0	30.7	30	0.5	10	- 20 to 55	5700
Purple	Ø 1.2	0.358	0.233	14.2	21.5	30	0.5	10	- 20 to 55	5700
Pink	Ø 1.2	0.413	0.287	19.5	29.7	30	0.5	10	- 20 to 55	5700
Aqua	Ø 1.2	0.171	0.520	100.0	155.7	30	0.5	10	- 20 to 55	5700
Green	Ø 1.2	0.128	0.566	64.0	98.0	30	0.5	10	- 20 to 55	5700
Blue	Ø 1.2	0.097	0.409	36.2	66.9	30	0.5	10	- 20 to 55	5700
Gold	Ø 1.2	0.472	0.510	70.8	109.2	30	0.5	10	- 20 to 55	5700

All values are to be used as average values / typical ranges \pm 20% measured at 20°C

* lifetime based upon operation cycles: 6 hours on, 18 hours off - reaching 30% of the initial brightness.

Average AC current: 120 mAmp, Input Voltage: 90VAC (rms)

Insulation Breakdown Voltage: 4,000 Volts per IEC 335-1

Colour	Mid Europe - Approximate time to discoloration after average sunlight exposure dose (months)	Tropical Area - Approximate time to discoloration after average sunlight exposure dose (months)
Aqua	24	12
Blue	24	12
White	18	9
Green	18	9
Pink	8	4
Red	6	3

Olmec Advanced Materials Ltd/Surelight
12 terminus Road
Sheffield
S7 2LH, UK

GB VAT No. 570 6797 06
Company Reg No. 247 6257



Tel: +44 (0) 114 236 1606

Fax: +44 (0)114 262 1202

Email: info@surelight.com

Website: www.surelight.com

Certificate No. 1644/98